NOUVEAU 7 | Technical Data (PLANK)

PRODUCT INFORMATION:

| Plank Size (Length x Width x Height) | Edge Profile | Finish | Construction | Gloss Level | Installation | Species |
|---|---------------|-----------|-------------------------|-------------|------------------------------|-----------------------|
| 7-1/2"Width x 3/4"Thick x (12"-72")Length | 4 Sides Bevel | UV Finish | Multi-Layer Ply Core | 5-10° | Nail, Glue-Down, Floating | European Oak, Hickory |

| WARRANTY: | | | PAC | PALLET: | | | |
|-------------|------------|----------------------|------------------------------|--|--------------------------|-----------------------|------------------------------|
| Residential | Commercial | Planks Per Carton | Square Footage Per Carton | Carton Dimensions (Length x Width x Height) | Carton Weight | Cartons per Pallet | Square Footage Per Pallet |
| 30 Years | 5 Years | 5 | 19.84 sqft | L1930mmXW200mmXH98mm | 46.52 lbs (21.10 kgs) | 50 | 992 sqft |

| Dimensional Characteristics and Limit Deviations | | | | | |
|--|--------------------------------|------------------------------|--------------------------------------|---------------|--|
| Deviation | Deviation of Length | | ≤0.1% of length up to 1mm maximum | Pass | |
| Deviation | Deviation of Width | 7 | ±0.20mm | Pass | |
| | Deviation of Thickness | | ±0.25mm | Pass | |
| Bow | Convex | | ≤1.0% | Pass | |
| BOW | Concave | EN 13647-2011 | ≤0.50% | Pass | |
| C:::= | Convex | ANSI-HPVA EF 2012 | ≤0.20% | Pass | |
| Cup | Concave | | ≤0.15% | Pass | |
| Height | Height Difference | | ≤0.20mm | Pass | |
| Opening Betwe | Opening Between Elements (Gap) | | ≤0.15mm | Pass | |
| S | Spring | | ≤0.3mm | Pass | |
| Straightness | | ĺ | ≤0.2mm | Pass | |
| T&G or Click System | | Per Product Specification of | Perfectly Match Master Samples | Perfect Match | |
| B . I | | BMCI | Perfectly Match Master | D (| |

| Testing Results | | | | | | |
|-----------------------------------|---------------------------|--|--------|--|--|--|
| Reference | Standard | Test Request | Result | | | |
| Abrasion Resistance | ASTM D4060 | ≥130 cycles | Pass | | | |
| Adhesion | ASTM D3359 | ≥4B | Pass | | | |
| Moisture Content | ASTM D4442 | 6%-10%, Ave≤9% | Pass | | | |
| E-Rating (Formaldehyde Emissions) | ASTM D6007 | P2≤0.05ppm | Pass | | | |
| Immersion-Peel Test | ASTM D4222 | No Peeling | Pass | | | |
| High-low Temperature Cycle | ASTM D1211-1997 | Without clear blister or crack after 8 cycles or more | Pass | | | |
| Modulus of Elasticity (MOE) | GB/T 17657-2013 | ≥4000 Mpa | Pass | | | |
| Modulus of Rupture (MOR) | GB/T 17657-2013 | ≥30 Mpa | Pass | | | |
| Gloss Value | As customer's requirement | 5~10° | Pass | | | |
| Hardness of Coating | ASTM D3363-2005 | ≥2H | Pass | | | |
| Scratch Resistance | EN 438 | ≥2N | Pass | | | |
| VOC | Floorscore | Floorscore Certified | Pass | | | |

www.BIYORKCANADA.com

Biyork product specifications are subject change. Please always refer to a physical sample for reference. All Rights Reserved 2020.